



Polychlor

# ANALYTICAL TEST REPORT

Date

REPORT NO. :

PARTY'S NAME :

PRODUCT : CHLORINATED PARAFFIN (CP)

Polychlor 50 - PCSO (1300)

BATCH NO. :

QUANTITY :

TRUCK No. :

DESCRIPTION : Clear Transparent Liquid Free From Sediments And Suspended Matter

Sr. No.	Particulars	Test Method	Results
1.	Grade as per	IS 14426:1997	III
2.	Colour (HU)	ASTM-D1045-86	30
3.	Specific Gravity (at 27°C)-(at R. Temp)	ASTM-D-1045	1300
4.	Chlorine Content (% W/W)	ISI 1448-77	50
5.	Viscosity (at 27°C) Poise	Brook Field Viscometer	20
6.	Free Mineral Acidity; %	SG/QC/CP-01	0.00010
7.	Free Chlorine	ISI-9189-79	NiL
8.	Volatile Loss (180° C/4 Hrs); %	SG/QC/CP-02	4.2
9.	Thermal Stability (175° C/4 Hrs); %	SG/QC/CP-04	0.180
10.	Heat Stability (180° C/ 20 Min.)	SG/QC/CP-03	Light Brown
11.	Refractive Index (at 27°C)	ASTM-D-1807	1.592
12.	pH Value	SG/QC/CP-05	6.0.

(Chemist)

(Approved By)