

EVA 台塑烯乙烯 - 醋酸乙酯共聚物



台塑烯 乙炔醋酸乙酯共聚物 (EVA) 採用 Enichem 高壓製程技術生產，此製程包含管式法及槽式法。目前台塑烯 EVA 能提供VA含量最高達33%的多樣應用品別，來滿足客戶多樣變化需求。

台塑烯 EVA 具備異加工特性、光學性質、低溫韌性、耐化學性、交聯發泡性，使台塑烯 EVA 能廣泛應用於溫室棚膜、積層包裝膜、農業用膜、一般包裝膜、押出及射出及鞋材發泡、熱熔膠等產品應用。

台塑烯 EVA 所有品別均符合美國 FDA 21-177-1350規範以及歐盟限制危害物質限令(RoHS)。

TAISOX® Ethylene Vinyl Acetate Copolymer

TAISOX® Ethylene Vinyl Acetate Copolymer (EVA) resin is produced via high pressure process technology from Enichem, Italy. It has two processes including tubular process and autoclave process. TAISOX® EVA now produces various EVA copolymers grades with vinyl acetate(VA) content up to 33% to satisfy diverse demands of customers.

TAISOX® EVA has excellent processability, transparency, low temperature sealing, chemical resistant, and crosslinking foaming. It can be used for many applications such as greenhouse film, laminated film, agricultural film, packaging film, extrusion, injection molding and expanded foam (shoes, soles), hot melt applications etc.

All EVA products complies with U.S. FDA 21-177-1350, RoHS.



乙炔 - 醋酸乙酯共聚物(EVA)

品別 Grade	基本物性 Basic Properties 單位 Unit	熔融指數 Melt index MI _{2.0} g/10min	密度 Density g/cm ³	VA 含量 Vinyl Acetate content %	拉力降伏強度 Tensile strength at yield	拉力斷裂強度 Tensile strength at break	斷裂伸長率 Elongation at break	硬度 Hardness Shore A/D	熔點 Melting point °C	結晶點 Freezing point °C	軟化溫度 - 維氏法 Softening point Vicat °C	軟化溫度 - 環 & 球 Softening point Ring-and-Ball °C	落球衝擊強度 Dart drop test g	用途 Application
薄膜級 Film	7350F	1.8	0.938	18	45	150	800	88 / 38	84	—	—	—	650	發泡鞋材、醫藥用途、吸震材料、PEVA 膠布 Greenhouse film, Sanitary applications, Gaskets, PEVA sheeting.
射出級 & 發泡級 Injection & Foaming	7240M	1.5	0.935	15	55	150	700	92 / 42	87	—	—	—	—	發泡鞋材、交聯發泡板 X-linked Foam - Sandal, Slipper.
	7320M	4.0	0.930	9	60	140	700	96 / 46	96	—	—	—	—	可攜性物件、交聯發泡板 Flexible items, X-linked Foam
發泡級 & Foaming	7340M	2.5	0.934	14	80	140	700	96 / 45	90	—	—	—	—	可攜性物件、交聯發泡板 Flexible items, X-linked Foam
	7350M	2.5	0.938	18	45	150	800	88 / 38	84	—	—	—	—	發泡鞋材、吸震材料、PEVA 膠布 X-linked Foam-shoes, Mid-sole, Gaskets, PEVA sheeting.
封裝級 Encapsulant film	7360M	2.0	0.941	21	40	180	800	86 / 36	80	—	—	—	—	發泡鞋材、吸震材料、PEVA 膠布 X-linked Foam-shoes, Mid-sole, Gaskets, PEVA sheeting.
	7470M	7.0	0.948	26	30	140	800	82 / 32	76	—	—	—	—	發泡鞋材、吸震材料、PEVA 膠布 X-linked Foam-shoes, Mid-sole, Gaskets, PEVA sheeting.
熱熔膠級 Hot melt	7870H	35	0.945	28	—	80	800	70 / 20	69	—	—	—	—	EVA 封裝膠的基礎原料 General-purpose for producing solar cell encapsulant film.
	7760H	25	0.945	28	—	82	800	70 / 20	70	51	36	84	—	—
	7A50H	150	0.934	19	—	70	700	73 / 23	82	62	43	92	—	書籍裝訂膠、自動包裝膠、合板膠、熱熔膠環 packaging bookbinding woodworking various assemblies
7A60H	150	0.938	28	—	40	800	67 / 16	71	50	33	81	—	—	

以上數據為測試平均值，僅提供參考。Data shown are average values and should not be examined for specifications.

台灣塑膠工業股份有限公司 聚烯事業部 Formosa Plastics Corporation, Polyolefin Division

修訂日期 (revised) 2011.06.01 www.fpc.com.tw / PE / index.htm